

MARKCHEM SUPERBOND LATEX

(STYRENE BUTADIENE LATEX FOR WATERPROOFING AND REPAIRS)



DESCRIPTION

MarkChem Superbond Latex is based on modified styrene butadiene latex supplied as a ready to use bonding agent in liquid consistency. It is used for repair of spalled concrete – floors, columns, beams, chhajas, slabs. Waterproofing of toilet, bathrooms and small terraces etc. It bonds strongly to old & new concrete and to plasters. It reduces shrinkage, prevents cracking, dust pick up & improves abrasion resistance.

FEATURES / ADVANTAGES

- Non-toxic to human being
- It acts as anti-corrosive for steel. SBR is highly durable even in continuous contact with water
- Multipurpose – it is multipurpose & economical product, easy to use
- Cracking – it prevents cracking by improving flexural strength
- Hardness – improves the hardness & prevents dust generation
- Shrinkage – Reduces drying & aging shrinkage cracks
- Bonding – Bond strongly to concrete, masonry, stonework, plasters, cementitious surfaces, asphalt & most of the building materials
- Abrasion resistance – improves abrasion resistance of the cement mix
- Reduces viscosity of cement injection grout for better fluidity & bonding

APPLICATIONS

- For concrete repairs - Spalled concrete of floors, columns, beams, chhajas, slabs, parapets, etc
- For waterproofing – Small roof terraces, sunken portions of toilets & bathrooms, chhajas & lift pits, balconies & staircases
- Renovation and protection of concrete against corrosion and salt petre.
- For waterproofing – liquid & effluent tanks, car decks & walkways.

- Bonding mortar for tiles & panels, as undercoat for special finishes such as top rendering coat for chemical resistant floors.
- For bonding of new concrete to old concrete, masonry stone work, plastering.
- Fixing or re-fixing of slip bricks, tiles, stones & marble bedding.
- As external rendering – weatherproof & frost resistant render high wear & erosion resistant render. As bonding slurry coat for pinhole treatment on concrete surface & as repair mortar for overhead application.

DIRECTION FOR USE

SURFACE PREPARATION :- Clean the surface with wire brush or scrubber to remove hidden dirt, loose particles, laitance & dust. Degrease the surface by using suitable solvents.

- Repair the Spalled concrete portion by saw, cutting the extreme edges of the repair location to a depth of at least 10 mm to avoid feather-edging & to provide strong bond.
- Clean the concrete surface to remove any contamination where breaking is not possible. Roughen the surface by light scrubbing or grit blasting.
- Expose corroded rebar in the repairing area fully. Remove all loose scales & corrosion deposits and immediately clean the surface.

PRIMING:- For priming of concrete substrate, the surface should be thoroughly saturated with potable water. Remove any excess of water prior to application. Slurry of primer coat is prepared by mixing of one part MarkChem Superbond Latex, one part of water and 3 parts of fresh OPC cement. Slowly mix cement with binder to obtain a smooth consistency. Continue mixing the slurry during application to prevent settlement.

MIXING:- A forced action mixer is essential (Pan Mixer) & recommended to ensure that MarkChem Superbond Latex mortar is thoroughly mixed or Use a suitable sized drum with heavy-duty electrical drill machine fitted with

MARKCHEM SUPERBOND LATEX

(STYRENE BUTADIENE LATEX FOR WATERPROOFING AND REPAIRS)



APPLICATION COMPOSITIONS

SNO	APPLICATION	COMPOSITION	QUANTITY SUPERBOND LATEX	CONSISTENCY AND THICKNESS
1	Patching, Repair Mortar & Dry	OPC : 50Kg GRADED SHARP & WASHED & DRY SAND : 150 Kg Water : 10 Litres	10 Litres	Mortar consistency, 6-40 mm thickness
2	Heavy Duty Floor Screed	OPC : 50Kg Graded sharp & washed sand : 75 Kg Granite chips (3-6 mm) : 75 Kg Water : 6 Litres	10 Litres	Semi dry cohesive consistency, 10-40 mm thickness
3	Renders	OPC : 50Kg Graded sharp & washed sand : 150 Kg Water : 6 Litres	10 Litres	Mortar consistency, 6-9 mm thickness
4	Bonding Mortar for Slip Bricks & Tiles	OPC : 50Kg Graded sharp & washed sand : 125 Kg Water : 7 Litres	10 Litres	Mortar consistency, 6-40 mm thickness.

MARKCHEM SUPERBOND LATEX

(STYRENE BUTADIENE LATEX FOR WATERPROOFING AND REPAIRS)



spiral paddle mixer at slow speed of 400-500 rpm.

- Hand mixing is permissible only for 25 kg or less quantity.
- Charge the mixer with required quantity of clean & dry sand, cement & mix for 1-2 minutes, then adds MarkChem Superbond Latex as per the dosages recommended. Mix for 2-3 minutes to avoid air entrapment. Keep on slowly adding water until the required consistency is achieved. Do not add extra water.

TYPICAL CHARACTERISTICS

PROPERTIES	RESULTS
Base	SBR Latex
Total Active Solid Content	34 ± 2%
pH	8 - 9
Specific Gravity At 30°C	1.01 ± 0.02
Coverage	20 - 22 sq. ft./kg for two coats

SPECIFICATION COMPILES

- BS6319 part2:1983
- ASTM C – 190-85

PACKING

1 Litre, 5 Litre, 20 Litre, 200 Litre Plastic Container

SHELF LIFE

12 months in original unopened packaging when stored in cool and dry place. (Prevent From Direct Sunlight)

PRECAUTIONS

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

DISCLAIMER

The above information and details herein are based on the tests conducted & experience on application and usage. The user is advised to carry out the test and take trials to satisfy on the suitability of the products and meeting his requirement considering the prevailing conditions prior to apply/ using it on larger area. As the conditions under which the products are used or transported are beyond our control. We would not hold ourselves responsible on its consequential nonperformance.



MR MARK OVERSEAS

REGISTERED OFFICE

VIJAY NAGAR, NEAR NAMASTAY CHOWK, GT ROAD, KARNAL - 132001

(HARYANA) INDIA MOB : +91 8860760000, 9215703333

WEBSITE : WWW.MARKCHEMCONSTRUCTION.COM

EMAIL : INFO@MARKCHEMCONSTRUCTION.COM